

# **Technical Data Sheet**

Auto012 Fast Cure Epoxy

#### **PRODUCT DESCRIPTION**

Bondloc Fast Cure Epoxy is a 5 minute clear resin suitable for bonding a wide variety of surfaces.

### APPLICATIONS

suitable for bonding a wide variety of surfaces including wood, steel, fibreglass, carbon fibre, glass, leather rubber, cardboard, most plastics, aluminium and galvanised iron. Water resistant. Product reacts within a few minutes to give a tough resilient bond

#### **USEFUL HINTS/NOTES**

- Clean & easy to use
- Viscous but not thixotropic
- Rapid curing

#### **INSTRUCTIONS FOR USE**

- Ensure that surfaces to be bonded are clean and free from grease, dirt, dust and any other contamination.
- Mix equal quantities either by weight or volume of the two parts and stir thoroughly until a colour is obtained. Where a static mixing nozzle is supplied the 2 parts will be mixed correctly upon dispensing.
- Apply to one surface and offer up the second surface. Clamp or jig together under light pressure.

Leave to cure at room temperature.

#### STORAGE

Stored under dry conditions in closed containers between 5 and 25°C B2012 will have a shelf life of 12 months.

### **TECHNICAL FEATURES**

	Part 1	Part 2
Physical Form	Viscous liquid	Viscous liquid
Chemical Type	Ероху	Mercaptan and polyamide
Appearance	Clear	Clear
Mixed Viscosity 25°C	15,000 – 20,000 Pa.S	
Specific Gravity	1.1	
Mix Ratio	1:1vol/vol or wt/wt	
Work Life	As a mix: 5 mins	
Percent Solid	100	
Adhesive Set-up Time	2-3 hours.	

#### MECHANICAL PROPERTIES

WECHANICAL I NOI ENTES	
Shore Hardness D	78-80 (ASTM D
	2240)
Shear Strength (N/mm <sup>2</sup> )	14-18 (DIN 53283)
Peel Strength (N/mm <sup>2</sup> )	3-5 (ISO 4578)
Thermal Conductivity	0.1
(W/mK)	
Coefficient of thermal	60-120 x 10 E <sup>-6</sup>
expansion (1/k)	
Dielectric Strength (kv/mm)	50-90
Volume Resistivity	3-5 x 10 E <sup>12</sup>
(OHM/cm)	
Service Temperature	-40°C to +121°C
	(-40°F to 250°F)

Bondloc UK Ltd. Units 1 & 2 Bewdley Business Park Bewdley, Worcestershire DY12 2TZ, UK

+44 (0) 1299 269 269 sales@bondloc.co.uk PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Safety Data Sheets (SDS) for this and all other products being used are understood by all persons who will work with the product. Warranty: All products purchased from or supplied by Bondloc are subject to terms and conditions set out in the contract. Bondloc warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Bondloc is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Bondloc makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.



Revision:



## **Technical Data Sheet**

Auto012 Fast Cure Epoxy

#### **CURED PERFORMANCE**

Lap Shear Strength		
Substrate	Shear Strength/Failure Mode	
CRS/CRS	2,350 psi – Cohesive Failure	
Aluminium/Aluminium	1,950 psi – Cohesive Failure	
Copper/Copper	1,850 psi – Cohesive Failure	
FRP/FRP	900 psi – Cohesive Failure	
ABS/ABS	850 psi – Cohesive Failure	
Chemical Resistance		
Media	Lap Shear (ASTM D 1002) Strength in PSI	
Gasoline	2550	
Acetic acid (10%)	2180	
Xylene	2165	
Lubricating oil-HD30	2400	
Paraffin	2275	
Water @ 23 <sup>o</sup> C	2355	
Water @ 90⁰C	2325	

Plastics	Shear strength psi
ABS	210
GRP	540
HIPS	210
Nylon	180
Perspex	330
uPVC	170
Polycarbonate	240
Metals	Shear strength psi
Steel	550
Steel, abraded	900
Stainless steel	1050
Aluminium	650
Aluminium, abraded	960
Galvanised iron	800
Others	
Plywood	680
Teak	820

#### **HEALTH & SAFETY**

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS

### PACKAGING FORMAT

25ml

Bondloc UK Ltd. Units 1 & 2 Bewdley Business Park Bewdley, Worcestershire DY12 2TZ, UK

+44 (0) 1299 269 269 sales@bondloc.co.uk PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Safety Data Sheets (SDS) for this and all other products being used are understood by all persons who will work with the product. Warranty: All products purchased from or supplied by Bondloc are subject to terms and conditions set out in the contract. Bondloc warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Bondloc is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Bondloc makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.



www.bondloc-auto.com