

# **Technical Data Sheet**

# Auto72 Brake & Airline Sealant

#### PRODUCT DESCRIPTION

Brake and Airline sealant is an instant liquid sealant that replaces PTFE or other materials to form a seal against on metals parts where Water, Fuel & Oils its present will provide an instant seal and stop the corrosion of threads to enable future disassembly.

#### **APPLICATIONS**

Replaces tapes and dopes, stops gas and fluid leaks on most metals and assists in lubricating during assembly. Brake and Airline sealant will not shred or tear which would contaminate your system. Use Brake and Airline sealant to seal against oils, gases, chemicals, water and steam etc.

#### **USEFUL NOTES**

Wipe threads with clean shop cloth. Apply a continuous bead to 3rd or 4th thread depending on the thread length.

## **PROPERTIES**

Instantaneous low-pressure seal. No locking action up to 48 hours. Easy break loose allowing realignment.

#### **INSTRUCTIONS FOR USE**

Ensure parts are clean, dry and free from oil and grease.

#### PROCEDURE FOR APPLICATION

Apply only to clean, dry parts. Degreasing directly assists results.

#### **COMPATIBLE ACCELERATORS / PRIMERS**

None recommended.

### **STORAGE**

Store in a cool area out of direct sunlight.

Shelf Life > 12 months at ambient temperature.

#### **TECHNICAL FEATURES**

| Resin                                    | Modified<br>Dimethacrylate |
|--|----------------------------|
| Colour                                   | White paste                |
| Cure Speed with<br>Activator             | Not recommended            |
| Cure Speed without<br>Activator          | Up to 60 hours             |
| Viscosity Brookfield Sp3<br>@20rpm @ 25° | 20,000cps                  |
| Gap Fill / Max<br>Threadform             | 0.4 mm / M36               |
| Flash Point                              | >85°C                      |
| Shelf Life                               | 36 months @ 20°C           |
| Specific Gravity                         | 1.25                       |
| Max Operating<br>Temperature             | -55°C to + 150°C           |

## **CURED PERFORMANCE**

| Full Cure Time                  | 60 hours |
|---------------------------------|----------|
| Typical Breakaway ISO<br>10964  | 6 N.m    |
| Typical Prevailing<br>ISO 10964 | 2 N.m    |

### **HEALTH & SAFETY**

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS.

# **PACKAGING FORMAT**

50ml

Bondloc UK Ltd. Units 1 & 2 Bewdley Business Park Bewdley, Worcestershire DY12 2TZ, UK

+44 (0) 1299 269 269 sales@bondloc.co.uk PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Safety Data Sheets (SDS) for this and all other products being used are understood by all persons who will work with the product. Warranty: All products purchased from or supplied by Bondioc are subject to terms and conditions set out in the contract. Bondioc warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Bondioc is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Bondioc makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.

