



Technical Data Sheet

Auto001 Epoxy Repair Putty Steel

PRODUCT DESCRIPTION

Bondloc Epoxy Repair Putty is a steel-filled, professional epoxy putty for general maintenance and repairs.

APPLICATIONS

Excellent for filling holes in castings and rebuilding metal surfaces. Can be sanded, drilled, machine and painted once cured. It resists gas, oil, diesel, petrol, water and coolant (anti freeze). Can resist temperatures up to 100°C

INSTRUCTIONS FOR USE

Proper surface preparation is essential to a successful application. The following procedures should be considered: Degrease the surface, oil, grease and dirt must be removed before applying any epoxy material.

All surfaces must be thoroughly roughened ideally by grit blasting (8-40 mesh grit), or by grinding with a coarse wheel or abrasive disc pad. An abrasive disc may be used provided white metal is revealed. This creates increased surface area for better adhesion. A 3-5 mil profile is desired for an application. Do not "feather edge" epoxy materials. Epoxy materials must be "locked up" by defined edges and a good 3-5 mil profile. Metal that has been handling sea water or other salt solutions should be grit blasted and high-pressure water blasted and left overnight to allow any salts in the metal to "sweat" to the surface: repeat blasting to "sweat out" all the soluble salts. A test for chloride contamination should be performed prior to any epoxy application. The maximum soluble salts left on the substrate should be no more than 40p.p.m (parts per million).

Under cold working conditions, heating the repair area to 38°C - 43°C immediately before applying is recommended. This procedure dries off any moisture, contamination or solvents and assists the epoxy in achieving maximum adhesion to the substrate. All prepared surfaces should be repaired as soon as possible, to eliminate any changes or surface contaminants.

Epoxies are very good in water, saturated salt solutions, leaded gasoline, mineral spirits, ASTM # 3 oil and propylene glycol. Epoxies are generally not recommended for long term exposure to concentrated acids and organic

solvents. For immersion applications this product is not recommended.

Twist or cut off required amount from stick. Then knead with fingers to a uniform colour. All black colour dye must be gone and a uniform pure grey colour is left. Apply to surface to be repaired within 2 minutes of mixing. The mixed epoxy does not show much bond strength at this time, but can be kneaded or formed into any cracks or holes to be filled.

TECHNICAL FEATURES

Typical Properties	7 days cured at 24°C
Colour	Grey
Viscosity	Putty
Pot Life @24°C	20 mins
Comprehensive Strength	83 N/mm ²
Adhesive Tensile Shear	5 N/mm ²
Cured Hardness Shore D	75
Dielectric Strength volts/mil	300
Solids	100%
Temperature Resistance	121°C Continuous 149°C Intermittent

CHEMICAL RESISTANCE

7 days room temperature cure (30 days immersion)

10% Sulphuric Acid	Fair
10% Hydrochloric Acid	Fair
Chlorinated Solvents	Very Good
Methanol	Very Good
Toluene	Very Good
Ammonia	Very Good
10% Sodium Hydroxide	Excellent
Kerosene	Very Good

HEALTH & SAFETY

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS

PACKAGING FORMAT

50g

Bondloc UK Ltd.
Units 1 & 2
Bewdley Business Park
Bewdley, Worcestershire
DY12 2TZ, UK

+44 (0) 1299 269 269
sales@bondloc.co.uk

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Safety Data Sheets (SDS) for this and all other products being used are understood by all persons who will work with the product. Warranty: All products purchased from or supplied by Bondloc are subject to terms and conditions set out in the contract. Bondloc warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Bondloc is considered accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Bondloc makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.





Technical Data Sheet

Auto001 Epoxy Repair Putty Steel

Bondloc UK Ltd.
Units 1 & 2
Bewdley Business Park
Bewdley, Worcestershire
DY12 2TZ, UK

+44 (0) 1299 269 269
sales@bondloc.co.uk

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Safety Data Sheets (SDS) for this and all other products being used are understood by all persons who will work with the product. **Warranty:** All products purchased from or supplied by Bondloc are subject to terms and conditions set out in the contract. Bondloc warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Bondloc is considered accurate but is furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Bondloc makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.

